

### Geomembrane Chemical Resistance Comparison

	XR-5®	PVC	Hypalon	Polypropylene
<b>Kerosene</b>	A	C	C	C
<b>Diesel Fuel</b>	A	C	C	C
<b>Acids (General)</b>	A	A	B	A
<b>Naphtha</b>	A	C	B	C
<b>Jet Fuels</b>	A	C	B	C
<b>Saltwater 160°F</b>	A	C	B	A
<b>Crude Oil</b>	A	C	B	C
<b>Gasoline</b>	B	C	C	C

A = Excellent

B = Moderate

C = Poor

NF = Not Found in Published Chart